



## ENAR WELD BRAZE PVT. LTD

A-112, DDA INDUSTRIAL SHEDS,  
OKHLA INDUSTRIAL AREA, PHASE – II  
NEW DELHI – 110020

Telephone : 011-26383911/12/13  
Fax : 011-26383913  
E-Mail : info@enarweld.com

---

### ENAR CFB Paste: Copper Furnace Brazing Paste BCuSn4

#### Unique Features:

A typically formulated paste with 99.9 % + purity fine mesh Copper Alloy Powder having a metal content of 85% weight mixed with special binders.

#### Advantages:

This Copper Brazing Alloy is usually used for furnace brazing of Mild Steel, 300 & 400 series of Stainless Steels and Carbon Steels and High Alloyed Steels.

Copper Brazing paste has a good fillet forming property which gives a better appearance at the joints. It is recommended to be used in cracked Natural Gas or Propane, H<sub>2</sub>/N<sub>2</sub> atmosphere furnaces.

It is ideal for joints for elevated temperature services and for brazing Heat Exchangers and Joining Tubular components providing strong, leak-proof joints.

The brazing process has to be carried out in vacuum or controlled atmosphere.

**Brazing Temp:** 1060°C

This filler metal is very fluid and works best with joint clearances less than 0.02 to 0.15 MM.

#### Typical Chemistry of Deposit:

Composition, typical analysis (% w/w):		
Cu	Sn	Pb
95.90 – 96.00	4.00	<0.02

#### Unique Features:

- Extremely free and thin flowing for maximum capillarity.
- Self-fluxing properties.
- High degree of wetting & bonding.
- Strong, ductile & leak proof joints.

**Advantages:**

- Highly user friendly while dispensing.
- Precise, economical dosage even on small components.
- Pre-paste components can be stored for several hours prior to brazing operation.
- Clean binder with minimum smoke generation during furnace brazing.
- No post treatment or cleaning required after brazing

**Application / Dispensing:**

- Manually or automatically with pneumatical or mechanical dispensing units

**Physical Properties:**

Color:	Orange-Brown
Specific Gravity:	8.92
Density:	0.32 lb/in <sup>3</sup>
Electrical Conductivity:	101% IACS
Electrical Resistivity:	1.71m $\Omega$

**Standard Packing :** 5 / 10 Kgs. Plastic Pails.