



# KISWEL

## KISWEL K-410NiMoT

### Classifications:

EN ISO 17633-A:2008 : T 13 4 R M4  
EN ISO 17633-B:2008 : TS410NiMo-FM0

AWS A5.22-07 : E410NiMoT0-4  
JIS Z 3323 : TS410NiMo-FM0

### Typical Chemistry Composition of Weld Deposit:

C	Si	Mn	Cr	Ni	Mo
<0.06	<1.00	<1.00	11.00 – 12.50	4.00 – 5.00	0.40 – 0.70

### Description:

- K-410NiMoT is designed for MAG welding of soft-martensite stainless alloys of the 13%Cr-4%Ni-Mo types such as AISI 403, 405, 410, 420, JIS SCS3, SCS6, ASTM CA15M, CA6NM
- The said wire is a metal type of flux cored wire for flat and horizontal position welding.
- K-410NiMoT features very good ductility, CVN toughness and crack resistance.
- The machinability of the weld metal depends largely upon the kind of base metal and degree of dilution.

### Typical Mechanical Properties:

Yield Strength  
(Mpa)  
min. 500

Tensile Strength  
(Mpa)  
min. 760

Elongation  
(%)  
min. 15



**ENAR WELD BRAZE PVT. LTD**, Enar Chambers, A-112, DDA INDUSTRIAL SHEDS, OKHLA INDUSTRIAL AREA, PHASE - II, NEW DELHI – 110020 ☎ : 011-26383911 /12 /13 Fax : 011-26383913 e-mail : [info@enarweld.com](mailto:info@enarweld.com)  
**Exclusive Distributors of Kisel Ltd. Korea**