



KISWEL

KISWEL – K-91TB3

Classifications:

AWS A5.29: E91T1-B3C

JIS Z 3183: T62 T1-1C-2C1M

AWS A5.36: E91T1-C1PZ-B3LC

EN ISO 17634-A: T CrMo2L P C 1

Typical Chemistry Composition of Weld Deposit:

C	Si	Mn	Cr	S	Mo
0.05 – 0.12	<0.80	<1.25	2.00 – 2.50	<0.025	0.90 – 1.20

Description:

- For welding 2.25%Cr-1.0%Mo creep-resistant steel for fabrication of high pressure vessels and Piping systems.
- Excellent welding characteristic with low spatter and easy to remove slag.

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 540	min. 620	min. 18

Welding Parameters:

Wire Diameter	Welding Position	Shielding Gas	Current (A)		Voltage (V)	
			Min.	Max.	Min.	Max.
1.20 mm	F, HF	CO ₂	220	280	25	30
1.20 mm	VU		200	240	25	28
1.20 mm	OH		160	220	23	28



ENAR WELD BRAZE PVT. LTD, Enar Chambers, A-112, DDA INDUSTRIAL SHEDS, OKHLA INDUSTRIAL AREA, PHASE - II, NEW DELHI – 110020 ☎ : 011-26383911 /12 /13 Fax : 011-26383913 e-mail : info@enarweld.com

Exclusive Distributors of Kisel Ltd. Korea