



KISWEL

KISWEL – KD-B2

Classifications:

AWS A5.23: EB2
EN ISO 24598: S CrMo1 CS

JIS Z 3183: S572-1CM

Typical Chemistry Composition of Weld Deposit:

C	Si	Mn	Cr	S	Mo
0.05 – 0.15	0.05 – 0.30	0.45 – 1.00	1.00 – 1.75	<0.025	0.45 – 0.65

Description:

- For welding in power plants, heat exchangers and oil refinery applications for 1.25%Cr-0.5%Mo heat-resistant steel.
- Excellent mechanical and toughness properties after PWHT.
- Neutral flux for multi-pass welding.
- Excellent impact toughness and crack resistibility.

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)	Impact Value (J)
min. 590	min. 650	min. 27	100 (-20°C)

Packaging:

SAW Wire (Ø in mm): 2.40 MM / 3.20 MM / 4.00 MM / 4.80 MM in 25.00 Kg Spools

Welding Parameters:

Wire Diameter	Shielding Gas	Current (A)		Voltage (V)	
		Min.	Max.	Min.	Max.
2.40 mm	-	250	500	28	32
3.20 mm		300	650	28	32
4.00 mm		400	1200	30	34
4.80 mm		500	1400	32	36



ENAR WELD BRAZE PVT. LTD, Enar Chambers, A-112, DDA INDUSTRIAL SHEDS, OKHLA INDUSTRIAL AREA, PHASE - II, NEW DELHI – 110020 ☎ : 011-26383911 /12 /13 Fax : 011-26383913 e-mail : info@enarweld.com

Exclusive Distributors of Kisolw Ltd. Korea