



KISWEL

KISWEL – T-90SB3

Classifications:

EN ISO 21952-B: 2007: W 62 2C1M
AWS A5.28-05: ER90S-B3

KS D 7140: YGT2CM
JIS Z 3316: YGT2CM

Typical Chemistry Composition of Weld Deposit:

C	Si	Mn	P	S	Cr	Mo
0.07 – 0.12	0.40 – 0.70	0.40 – 0.70	<0.025	<0.025	2.30 – 2.70	0.90 – 1.20

Description:

- For butt and fillet welding of power plant, heat exchanger and oil refinery applications for 2.25%Cr-1.0%Mo heat-resistant steel.
- Excellent mechanical and toughness properties after PWHT.
- Proper tungsten electrode extension from the tip of torch is 4~6mm in general.

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)	Impact Value (J)
min. 540	min. 620	min. 17	180 (0°C)

Packaging:

GTAW Wire (Ø in mm): 1.60 MM / 2.00 MM / 2.40 MM / 3.20 MM in 5.00 Kg Packing

Welding Parameters:

Wire Diameter	Shielding Gas	Current (A)		Voltage (V)	
		Min.	Max.	Min.	Max.
1.60 mm	Ar	90	170	11	16
2.00 mm		90	180	12	18
2.40 mm		100	200	13	20
3.20 mm		120	250	13	22



ENAR WELD BRAZE PVT. LTD, Enar Chambers, A-112, DDA INDUSTRIAL SHEDS, OKHLA INDUSTRIAL AREA,
PHASE - II, NEW DELHI – 110020 ☎ : 011-26383911 /12 /13 Fax : 011-26383913 e-mail : info@enarweld.com
Exclusive Distributors of Kisol Ltd. Korea