



## ENAR NiCrMo-4 MIG / TIG Welding Wires

### Classifications:

ISO 18274: NiCr15Mo16Fe6W4/Ni 6276  
W.Nr.: 2.4819

AWS A5.14/ASME SFA-5.14: ERNiCrMo-4

### Typical Chemistry Composition of Weld Deposit:

C	Si	Mn	Cr	Ni	Mo	Fe	Cu
<0.02	<0.08	<1.00	14.50 – 16.50	Remainder	15.00 – 17.00	4.00 – 7.00	<0.50

### Description:

- EWB<sup>®</sup> 276 is a low carbon nickel-chrome-molybdenum alloy of type alloy C-276.
- The weld metal has high resistance in a wide range of media and exceptional resistant to pitting and crevice corrosion.
- It can also be used for dissimilar welding between nickel base alloys and stainless steels, as well as for surfacing and cladding.

### Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
470	750	40

### Packing Available:

**TIG Wire** (Ø in mm): 1.60 / 2.40 / 3.20 / 4.00

---

#### Enar Weld Braze Pvt. Ltd.

A-112, DDA Sheds Okhla Industrial Area,  
Phase-II, NEW DELHI – 110 020

e-mail: [info@enarweld.com](mailto:info@enarweld.com) web: [www.enarweld.com](http://www.enarweld.com)

**An ISO 9001:2015 Quality Management System Certified Co.**