



ENAR WELD BRAZE PVT. LTD

A-112, DDA INDUSTRIAL SHEDS,
OKHLA INDUSTRIAL AREA, PHASE – II
NEW DELHI – 110020

Telephone : 011-26383911/12/13
Fax : 011-26383913
E-Mail : info@enarweld.com

ENAR Ti-2

Classifications:

AWS A5.16: ER Ti-2
DIN 1737: SG Ti-2

Typical Chemistry Composition of Weld Deposit:

C	Fe	N	H	O ₂	Ti
<0.08	<0.25	<0.05	<0.013	<0.18	Remainder

Description:

- Titanium MIG/TIG wire for welding of pure Titanium and Titanium alloys with good elongation and medium strength.

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)	Hardness (HB)
275	400 - 540	20	180