



ENAR WELD BRAZE PVT. LTD

A-112, DDA INDUSTRIAL SHEDS,
OKHLA INDUSTRIAL AREA, PHASE – II
NEW DELHI – 110020

Telephone : 011-26383911/12/13
Fax : 011-26383913
E-Mail : info@enarweld.com

VENUS – ER 307

Classifications:

EN ISO 14343-A:2007 : G 18 8 Mn
AWS A5.9: ER307

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Si
<0.08	17.00 – 19.00	7.00 – 9.00	6.00 – 8.00	0.40

Description:

- MIG welding of 18%Cr-8%Ni-7%Mn austenite stainless steels.

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 350	min. 590	min. 25