



VENUS - ER 309LSi TIG / MIG / SAW Welding Filler Wires

Classifications:

EN ISO 14343-B: SS 309LSi
AWS A5.9: ER309LSi

KS D 7026: Y309LSi
JIS Z 3321: Y309LSi

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Si
<0.03	23.00 – 25.00	12.00 - 14.00	1.00 - 2.50	0.65 – 1.00

Description:

- For Welding of 22%Cr-12%Ni STS and dissimilar steels such as 304L to mild steels or low alloy steels.

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 350	min. 550	min. 35

Packaging:

MIG/MAG Wire (Ø in mm): 0.80 / 1.00 / 1.20 MM in 12.50 Kg Spools / 125 Kg Drums

TIG Wire (Ø in mm): 0.80 / 1.00 / 1.20 / 1.60 / 2.00 / 2.40 / 3.20 / 4.00 MM

SAW Wire (Ø in mm): 1.60 / 2.00 / 2.40 / 3.20 / 4.00 / 5.00 MM



ENAR WELD BRAZE PVT. LTD, Enar Chambers, A-112, DDA INDUSTRIAL SHEDS, OKHLA INDUSTRIAL AREA,
PHASE - II, NEW DELHI – 110020 ☎ : 011-26383911 /12 /13 Fax : 011-26383913 e-mail : info@enarweld.com

Exclusive Distributors of Venus Wire Industries Pvt. Ltd.
