



ENAR WELD BRAZE PVT. LTD

A-112, DDA INDUSTRIAL SHEDS,
OKHLA INDUSTRIAL AREA, PHASE – II
NEW DELHI – 110020

Telephone : 011-26383911/12/13
Fax : 011-26383913
E-Mail : info@enarweld.com

VENUS – ER 316L

Classifications:

EN ISO 14343-A: 2007: W 19 12 3 L
EN ISO 14343-B: 2007: SS 316L
AWS A5.9-07: ER316L

KS D 7026: 2005: Y316L
JIS Z 3321: 2008: Y316L

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Si	Mo
<0.03	18.00 – 20.00	11.00 – 14.00	1.00 - 2.50	0.30 – 0.65	3.00 – 4.00

Description:

- TIG welding of 18%Cr-12%Ni-2%Mo austenite stainless steels (AISI STS 316, 316L)

Typical Mechanical Properties:

Yield Strength
(Mpa)
min. 320

Tensile Strength
(Mpa)
min. 490

Elongation
(%)
min. 30